



Home | Search | Order | Shopping Cart | Login | Site Map | Help

Patria Plantes

ephon

(September)

iventars)

rinleants)

Kint



JP1308872A2: GRAPHITIC COMPOSITE MATERIAL

View Images (1 pages) | View INPADOC only

JP Japan

KUBOKI KOICHI FUJITA ATSUSHI NISHIDA TATSUYA

HITACHI CHEM CO LTD

News, Profiles, Stocks and More about this company

Dec. 13, 1989 / June 8, 1988

JP1988000140719

C04B 35/52; C01B 31/04;

Purpose: To provide a graphitic composite material having high strength and excellent impermeability to liquids, by bonding an expanded graphite sheet to a nonwoven fabric of inorganic or organic fiber, combined cloth or wire net as a lamellar reinforcing material with a resin and integrating.

Constitution: For example, nonwoven fabric of glass is impregnated or coated with an epoxy resin, which is dried and then made into a semicured state. An expanded graphite sheet is placed on one side of the nonwoven fabric and molded under pressure by heating to give a composite material. The expanded graphite sheet is bonded to the reinforcing material with the resin and integrated to develop high strength. The resin used for bonding not only bonds the expanded graphite sheet to the reinforcing material, but also is permeated into the interior of the expanded graphite sheet in the process of formation of the composite material and improves mechanical strength and impermeability to liquid of the expanded graphite sheet.

COPYRIGHT: (C)1989,JPO&Japio

DERABS C90-032457 DERC90-032457

Show the 1 patents that reference this one

Powered by DB7 and <u>Nel Data</u>

invention.

Olter/Abstract Inte

Foreign References

Alt mativ S arch s







Nominate this







GRAPHITIC COMPOSITE MATERIAL

Patent Number:

JP1308872

Publication date:

1989-12-13

Inventor(s):

KUBOKI KOICHI; others: 02

Applicant(s)::

HITACHI CHEM CO LTD

Requested Patent:

☐ JP1308872

Application Number: JP19880140719 19880608

Priority Number(s):

IPC Classification:

C04B35/52; C01B31/04

EC Classification:

Equivalents:

Abstract

PURPOSE:To provide a graphitic composite material having high strength and excellent impermeability to liquids, by bonding an expanded graphite sheet to a nonwoven fabric of inorganic or organic fiber, combined cloth or wire net as a lamellar reinforcing material with a resin and integrating.

CONSTITUTION: For example, nonwoven fabric of glass is impregnated or coated with an epoxy resin, which is dried and then made into a semicured state. An expanded graphite sheet is placed on one side of the nonwoven fabric and molded under pressure by heating to give a composite material. The expanded graphite sheet is bonded to the reinforcing material with the resin and integrated to develop high strength. The resin used for bonding not only bonds the expanded graphite sheet to the reinforcing material, but also is permeated into the interior of the expanded graphite sheet in the process of formation of the composite material and improves mechanical strength and impermeability to liquid of the expanded graphite sheet.

Data supplied from the esp@cenet database - 12

DOCKET NO: SGL

SERIAL NO:

APPLICANT:

LERNER AND GREENBERG P.A. P.O. BOX 2480 HOLLYWOOD, FLORIDA 33022 TEL. (954) 925-1100